

Sodium hypochlorite is a difficult chemical to handle in fiberglass reinforced plastic composite equipment. Not only are special fabrication techniques required, but the customer should also take special steps in their process to lengthen the service life of the FRP equipment.

The service life of FRP composite equipment can be seriously affected by those conditions that cause sodium hypochlorite to be "unstable". The definition of a "stable" sodium hypochlorite solution is a material which has a half life of at least 1,000 hours. Solutions manufactured and stored under the following conditions should have such an acceptable 1,000 hour half life:

| | |
|-----------------------|---------|
| Minimum pH | 11.0 |
| Maximum Temperature | 75°F |
| Maximum Metal Content | 0.1 ppm |
| Exposure to Sunlight | None |

Sodium hypochlorite that falls outside of the above limits can cause a serious reduction in service life of FRP composite equipment. Such service life could be as short as two to three years.

The temperature of the sodium hypochlorite has a tremendous affect on its stability. The following chart shows this temperature/stability relationship in terms of half life in hours.


| | | <u>Half Life (Hours)</u> | | |
|--------------|------|--------------------------|--------------|--------------|
| <u>NaOCl</u> | | <u>75°F</u> | <u>100°F</u> | <u>125°F</u> |
| 16.5% | 2150 | 150 | 25 | |
| 9.2% | 6000 | 1600 | 350 | |
| 5.0% | ---- | 2700 | 1000 | |

In addition, hypochlorite that is exposed to sunlight (ultraviolet rays) has a half life of just 192 hours. When exposed to sunlight, the sodium hypochlorite can quickly become unstable, with severe chemical attack occurring. This is one of the reasons that all bleach bottles are a solid opaque white. The white not only reflects the sunlight (ultraviolet ray exposure), but helps keep the contents cool.

All necessary process steps should be taken to ensure that the sodium hypochlorite is maintained at the lowest possible service temperature. In addition, no metal contact should occur with the liquid stream.

The following fabrication techniques must be employed for all FRP composite equipment used with sodium hypochlorite. These comments apply equally to pipe, as well as storage tanks.

All FRP composite equipment that is being used for sodium hypochlorite service should be pigmented a pure white throughout the entire structural portion of the laminate. This white must be such that the



equipment is entirely opaque. In addition, the white pigmentation helps minimize heat build-up from the sun.

For tanks, no sidewall flanged manways should be used. Only top access manways should be employed. These manways should be fitted with Monel bolts. Fittings in the sidewalls should be kept to an absolute minimum, and side and bottom drains should never be used. Electro wrap heating tape should not be used as an accessory on sodium hypochlorite tanks or pipe.

If necessary, to reduce summer temperatures, and to keep the product from freezing in the winter, insulation should be used as is appropriate on tanks and pipe.


For sodium hypochlorite service, we recommend that a premium grade vinylester resin (such as the Hetron 922, Derakane 411, Kopper's 9100, etc.) be used for the resin matrix.

Special laminate fabrication procedures are required for all FRP composite equipment that is to be used for sodium hypochlorite service. These techniques include:

1. The use of a double Nexus or synthetic veil (with a minimum total of 30 mils thickness) in the inner corrosion barrier. Just one layer of Nexus veil is not adequate for this chemical application.
2. Behind the double Nexus interior corrosion barrier must be a full SPI 90 to 100 mil thick fiberglass chopped strand reinforced corrosion liner.
3. The resin used for the internal corrosion barrier and liner should be catalyzed or reacted with a benzoyl peroxide (BPO)-DMA cure system. Cure systems based on standard MEKP catalysts should not be used for sodium hypochlorite service.
4. After completion of the entire vessel or pipe, a separate post-cure must be used. This post-cure can be either by use of steam, or where the tank and/or pipe is put into an oven and thoroughly post-cured. This post-curing at elevated temperatures must occur for at least 16 to 20 hours at 160°F, or from four to eight hours at 180°F.

Typically, PVC pipe is used for sodium hypochlorite service. We understand that PVC pipe typically provides good service life for sodium hypochlorite. Obviously, PVC pipe is significantly less expensive than FRP composite pipe.

However, if there are other circumstances that dictate the use of FRP pipe - such as its ability to handle mechanical abuse, higher pressures, long spans, etc. - you may want to consider the option of using FRP armored or overwrapped PVC pipe and fittings. In the last two years, we have built significant quantities of such FRP armored PVC pipe for similar services. The armored PVC product has been performing extremely well. This dual laminate combines the best of both worlds; using the PVC as the internal corrosion liner/barrier and the FRP as a structural portion of the wall.



Industrial Fiberglass Specialties, Inc.

521 Kiser Street
Dayton, OH 45404-1641
Tel: 937-222-9000
Fax: 937-222-9020

***Sodium Hypochlorite
Chemical Service
Environment***

09-25-92

Page #3 of 3

With this approach, there is no need for the Nexus corrosion barrier followed by the 100 mil liner, or for the special curing systems and post-cure. The FRP structural laminate becomes just that - an overwrap that provides the strength and mechanical protection. The PVC inner pipe is a completely integral pipeline that handles the corrosive service environment. We can provide not only the armored pipe, but all styles of pipe fittings and flanges with the FRP backing or structural laminate.