



# *Industrial Fiberglass Specialties, Inc.*

521 Kiser Street

Dayton, Ohio 45404-1641

Telephone (937) 222-9000 - Fax (937) 222-9020

## **Series 5970 FRP Composite Fire Retardant Pipe, Duct, and Fittings**

**For corrosive industrial service where high temperature, reasonable solvent resistance, and fire retardant properties are important.**

---

### **Uses and applications:**

Chemical plant process piping  
Fire retardant corrosion resistant fume duct  
Organic chemicals  
Acid drains  
Corrosive and abrasive slurries  
Waste water and sewage systems  
Chlorine and chlorinated water  
Water treatment piping  
Brine and brackish water  
Hazardous waste piping  
Piping & duct systems for combinations of solvents, acids, & bases.  
An alternative to costly alloys and specialty metals  
Industrial service for severely corrosive liquids

---

### **Description:**

### **Composition:**

Filament-wound fiberglass reinforced methacrylate modified epoxy composite pipe. ASTM D-2996 Classification Type I, Grade 2, Class E. Nominal 30 mil glass veil reinforced inner corrosion liner, followed by a nominal 20 mil corrosion liner reinforced with Nexus surfacing veil, followed by a fiberglass filament wound structural overwrap. A premium grade fire-retardant high-temperature high performance vinylester resin (Derakane 510-N, or equal), pigmented light gray for UV inhibition, is used in the corrosion barrier/liner; and for for the filament wound structural overwrap. Antimony trioxide is added to all resin, to achieve an ASTM E-84 flame spread rating of 25, or less. Operating temperatures up to 250° F.

---

### **Pipe & Duct Sizes:**

### **Pipe & Duct Lengths:**

137+ different diameters, ranging from a teeny 3/8" dia. up to a mammoth 168" dia. Pipe available built to iron pipe outside diameters (ASTM D-2996, Table 3), as well as pipe built to chemical process piping inside diameter standards. A current list of pipe sizes is available upon request. New sizes are being added regularly.

1/2" dia. pipe and smaller is built in 5 ft. lengths.

3/4" & 7/8" dia. pipe is built in 7 ft. lengths.

1" through 1-1/2" dia. pipe is built in 10 ft. lengths.

2" through 6" dia. pipe is available in 20 ft. lengths.

8" dia through 120" dia. pipe is available in 40 ft. lengths.

---

**Performance:**

Good corrosion resistance over a wide temperature range.  
Temperatures from sub-zero to 225°F.

**Advantages:**

Working pressures from NBS-PS-15-69 duct to 450 psi+, depending upon size and wall thickness.

Vacuum to -14.7 psig for all sizes, by selection of wall thicknesses, ribs and filament wind angle.

Available for earth burial, all depths, with selection of wall thicknesses, ribs and filament wind angle.

Weighs 1/6 as much as steel. Thus, lower installed costs.

Smooth inner surface produces very low frictional loss for reduced pumping and fan blower costs. Hazen-Williams flow coefficient under 150.

Recommended for a wide range of corrosion applications. Consult with Industrial Fiberglass Specialties, or the resin manufacturer, for specific project recommendations.

---

**Joining systems:**

Bell (socket) and spigot structural adhesive weld bonded joints. Adhesive bonded joints are available as your choice of straight/straight, straight/taper and taper/taper.

Threaded joints (NPT) through 12" dia. Other thread configurations available upon special order.

Flanges, all sizes through 84" dia. Including the superior filament wound socket flanges for sizes through 1/2" dia. through 36" dia. ANSI 150 lb., 300 lb. and 600 lb. all available as standard. Any pressure rating and drilling pattern available on order.

Van Stone, loose ring style, flanges.

Flange Spacers - all diameters, bolt hole patterns and thicknesses, built to order.

Bell and spigot O-Ring joints, thru 84" dia.

Bell and spigot O-Ring joints with locking key for restrained ends.

Mechanical Couplings, including Victaulic and Taylor-Kerr.

Expansion Joints, including triple O-Ring style for fly ash lines.

Speed-Seal O-Ring true unions.

Repair (maintenance) couplings.

---

**Physical Properties:****Mechanical Properties:**

See Table 1 for typical physical properties of Series 5970 FW FRP Pipe. These are conservative properties that can be used for the design of FW pipe for pressure, vacuum, supported span and burial conditions. Contact Industrial Fiberglass Specialties, Inc. for recommendations on the appropriate design formulas to be used for FRP composite pipe.

---

**Burial installations:**

As a custom manufacturer of pipe and fittings, we can design and build pipe to handle burial conditions ranging from live loads due to highway and rail traffic - to earth loads of 100 ft. or greater. We even have experience with underwater installations. Our engineers will welcome the opportunity to work with you on a pipe design, backfill selection and installation methods to meet your specific requirements. The result will be your lowest cost per year of service life (installed basis).

---

**Supported span installations:**

Again, we can design and build pipe to provide you the lowest cost for supported span installed pipe. Since we are not limited to just a few pipe wall thicknesses and filament winding angles - we can select and choose the combination of pipe design and support design and cost that will provide your "best buy". Consult with our engineers for help with your specific requirements.

---

**Fittings:**

Elbows, standard are 22-1/2°, 30°, 45°, and 90°. Any angle elbow available on special order. Elbows through 48" dia. are available as smooth radius. Mitered elbows are available in all sizes.

Reducing elbows

Tees

Reducing tees

Concentric taper body reducers

Eccentric taper body reducers

Saddles, with FRP and stainless steel threaded outlets, bell outlets, spigot outlets and flanged outlets.

Wear pads (blank saddles)

Crosses

Reducing Crosses

Laterals

Reducing Laterals

True wyes.

P-Traps and 180° U-Bends.

Floor drains

Expansion joints

Pipe couplings

Threaded (NPT) couplings

Adapters, bell by NPT thread (male or female threads available).

Adapters, spigot by NPT thread (male or female threads available).

Pipe nipples

Threaded nipples

Reducing bushings and threaded adapter bushings.

Fitting and pipe plugs. Pipe caps.

Blind flanges

Threaded flanges

Reducing flanges

Orifice flanges

All fittings are available as adhesive socket, plain end, flanged end, bell and spigot O-Ring; or any combination. See full Industrial Fiberglass Specialties' catalog for sizes, dimensions and tolerances. Fittings are available from 1/2" dia. through 84" dia. We welcome the opportunity to work with our customers on special fittings.

Table 1

***Industrial Fiberglass Specialties, Inc.***

521 Kiser Street - Dayton, Ohio 45404-1641  
Telephone (937) 222-9000 - Fax (937) 222-9020

**Properties of Series 5970 FW FRP Pipe & Duct**

Corrosion Barrier..... 30 mil C-Veil Reinforced  
Corrosion Liner..... 20 mil Nexus Veil Reinforced  
Resin (Barrier/Liner)...High Temp & High Performance FR Vinylester  
Structural Wall.....Filament Wound Overwrap  
Resin (FW Overwrap).....High Temp & High Performance FR Vinylester

**Elastic and Strength Properties of Glass Filament Reinforced Wall**

**Hoop Tensile: (Based on loading of pipe hydrostatically)**

Ultimate (porosity)..... 20,000 psi  
Yield..... 12,800 psi  
Allowable..... 6,700 psi  
Modulus of Elasticity..... 3,600,000 psi

**Tensile: (Based on loading of pipe as a tension member)**

Ultimate (rupture)..... 12,200 psi  
Yield..... 5,000 psi  
Allowable..... 3,300 psi  
Modulus of Elasticity..... 1,800,000 psi

**Flexural: (Based on loading of pipe as a beam)**

Ultimate (rupture)..... 15,700 psi  
Yield..... 6,100 psi  
Allowable..... 4,000 psi  
Modulus of Elasticity..... 1,700,000 psi

**Torsion: (Based on loading of pipe as a shaft in torsion)**

Ultimate (rupture)..... 16,200 psi  
Allowable Shear..... 5,500 psi  
Shear Modulus..... 750,000 psi

**Compression: (Based on loading of pipe as a "short" column)**

Ultimate (rupture)..... 11,200 psi  
Yield..... 7,000 psi  
Allowable..... 3,700 psi  
Modulus of Elasticity..... 1,400,000 psi

**Thermal Properties:**

Coefficient of Thermal Expansion..... 0.0000085 in./in./deg. F  
Thermal Conductivity..... 2.3 BTU/hr./sq. ft./deg. F/in. thick.